

| Article name | Fabric Composition | Fabric Thickness | Weight   | Humid Environment | PVC Free | Halogen Free | Light fastness | Cleaning advise | FR |
|--------------|--------------------|------------------|----------|-------------------|----------|--------------|----------------|-----------------|----|
| Reggio       | PES                | 0,35 mm          | 195 g/m2 | yes               | yes      | yes          | 5-6            | Damp cloth      | B1 |

| Colour code | Colour description | Fabric width in cm | Solar        |                    |                   | Light        |                    |                   | UV           |                    |                   | G <sub>tot</sub> value | Fc value |
|-------------|--------------------|--------------------|--------------|--------------------|-------------------|--------------|--------------------|-------------------|--------------|--------------------|-------------------|------------------------|----------|
|             |                    |                    | Transmission | Reflection Outdoor | Reflection Indoor | Transmission | Reflection Outdoor | Reflection Indoor | Transmission | Reflection Outdoor | Reflection Indoor |                        |          |
| 35700       | white              | 8,9/12,7/200       | 20%          | 70%                | 70%               | 19%          | 81%                | 81%               | 0.1%         | 6%                 | 7%                | 0.35                   | 0.50     |
| 35701       | yellow             | 8,9/12,7/200       | 21%          | 63%                | 63%               | 19%          | 74%                | 74%               | 0.1%         | 6%                 | 8%                | 0.38                   | 0.55     |
| 35702       | dark yellow        | 8,9/12,7/200       | 18%          | 60%                | 60%               | 15%          | 70%                | 69%               | 0.1%         | 7%                 | 6%                | 0.39                   | 0.56     |
| 35703       | green              | 8,9/12,7/200       | 15%          | 58%                | 58%               | 9%           | 60%                | 60%               | 0.0%         | 6%                 | 7%                | 0.40                   | 0.57     |
| 35704       | blue               | 8,9/12,7/200       | 14%          | 47%                | 48%               | 2%           | 30%                | 32%               | 0.1%         | 6%                 | 7%                | 0.45                   | 0.64     |
| 35706       | dark beige         | 8,9/12,7/200       | 12%          | 44%                | 43%               | 8%           | 48%                | 47%               | 0.2%         | 8%                 | 6%                | 0.46                   | 0.66     |
| 35707       | light grey         | 8,9/12,7/200       | 12%          | 51%                | 52%               | 8%           | 55%                | 57%               | 0.1%         | 6%                 | 7%                | 0.43                   | 0.61     |
| 35708       | dark grey          | 8,9/12,7/200       | 3%           | 26%                | 28%               | 1%           | 28%                | 30%               | 0.0%         | 6%                 | 7%                | 0.53                   | 0.76     |
| 35709       | soft beige         | 8,9/12,7/200       | 14%          | 56%                | 55%               | 10%          | 62%                | 62%               | 0.1%         | 7%                 | 6%                | 0.41                   | 0.58     |
| 35724       | vanilla            | 8,9/12,7/200       | 26%          | 65%                | 65%               | 25%          | 75%                | 75%               | 0.4%         | 9%                 | 7%                | 0.38                   | 0.54     |
| 35725       | grey               | 8,9/12,7/200       | 10%          | 45%                | 46%               | 5%           | 46%                | 48%               | 0.1%         | 6%                 | 7%                | 0.45                   | 0.65     |

Optical data (transmittance and reflectance) according to EN 410

Calculations according to EN 13363-1 (double clear glass low-E coating)

۱۹)